

Product Data Sheet

No. **26075** - 10/17

DRY FILM LUBRICANT

AEROSOL

PRODUCT NUMBERS: 6075

I. GENERAL DESCRIPTION

Description: A non-staining product that forms a slippery layer of translucent particles on rubber, wood, metals, nylon, epoxies, polypropylene, acrylics, and phenolic resins. Dry Film Lubricant is a dispersion of white, waxy particles of PTFE. For industrial use in manufacturing facilities. Not for retail sale.

Benefits: This film has unique dry lubricating qualities. Excellent for temperatures up to 500°F for extended periods. This product reduces clean-up labor time and will not interfere with post-finishing operations.

Application: This product is ideal for extreme dust conditions, such as encountered in mining and quarry operations. Use on conveyors, chutes, precision and electrical equipment.

Directions: Shake can well. Hold 8 to 10 inches from surface and apply uniformly. For best results, can should be at room temperature 70°F (21°C). Do not use on electrical equipment or machinery while in operation.

Limitations: Please refer to the Safety Data Sheet for specific information on material hazards, etc.

Packaging:

Cans - (16 oz.)	11 oz. net wt.. (312 g)	14.6 fl. oz. (446 mL)
Case - 12 cans/case	13 lbs. (5.9 kg)	0.55 CF (0.016 CM)



AerVOE Industries, Inc.
P.O. Box 485, Gardnerville, NV 89410



(775) 783-3100 Phone • (775) 782-5687 Fax • (800) 227-0196 Customer Service
www.aerVOE.com • mailbox@aerVOE.com

II. CHARACTERISTICS & PROPERTIES

Specifications:

None

Appearance:

Non-foaming liquid

Color:

Light milky

Odor:

Ketone

Dry Schedule:

Not Applicable

Performance and Chemical Properties:

Weight per gallon	5.8 lbs
Specific gravity	0.70
Viscosity	N/A
Flammability: Label marking	Extremely Flammable
Flash point	<0°F (-18°C)
Operating temperature range	40°F to 110°F (5° to 43°C)
Active ingredients by weight	2%
Volatile Organic Compound Level	70%
EPA VOC% Limit	Not Regulated
CARB VOC% Limit	I&I Exempt
Dielectric strength	TBD
Lubricity (FALEX FLC Test)	200 ft. lbs.
Penetrating ability	Excellent
Corrosion protection	Good

Base Materials:

..... PTFE, Acetone

Propellant:

..... Hydrocarbon

III. SHIPPING, STORAGE AND HEALTH

UN number	UN1950
Proper Shipping Description	Aerosols
Hazard Class	2.1
Packing Group	N/A
Limited Quantity	Yes
Warehouse storage level number	NFPA 30B Level 2
Storage temperature	32° to 120°F (0° to 49°C)
Shelf life	1 to 5 years
HMIS ratings	
Health	2
Fire	4
Reactivity	1

IV. MISCELLANEOUS

Contains no Ozone Depleting Substances (O.D.S.)

V. WARRANTY

1-year performance warranty on all products from date of purchase. Report to home office or local Aerove representative for examination. Because Seller cannot control Buyer's handling or use of product, Seller makes no warranty expressed or implied when not used or stored in accordance with directions. Seller shall not be liable for cost of labor, incidental or consequential damages, and this warranty is limited to replacement of product or credit of purchase.