

RUST-OLEUM®

V2100 SYSTEM RUST REFORMER®

DESCRIPTION AND USES

Rust-Oleum® High Performance Rust Reformer® is a specially formulated coating containing a silane additive which is capable of reacting with iron oxide in the rusted steel. Once reacted with iron oxide, the desiccant action of the silane helps inhibit further oxidation. Rust Reformer is for use on sound rusted steel surfaces and is not intended for use on clean metal or galvanized steel. The material dries to a hard black finish. A top coat is optional.

PRODUCTS

215634 V2100 System Rust Reformer®

PACKAGING

15 fl. oz. container, 6 aerosols packed to a carton

OPTIONAL TOPCOAT

V2100 System Enamel Aerosol

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter Original Cleaner/Degreaser or other suitable cleaner. Mold and mildew must be cleaned with a chlorinated cleaner or bleach solution. Rinse with fresh water and allow to dry.

Hand tool (SSPC-SP-2) or power tool (SSPC-SP-3) clean to remove loose rust to get to a sound rusted surface.

APPLICATION

Use when temperature is above 35°F (2°C) and humidity is below 85% to ensure proper drying. The surface temperature must be between 35-100°F (2-38°C). Use reformer on rusted surfaces. Protect surrounding surfaces from overspray. Overspray can carry a significant distance. Shake can for one minute after mixing ball is heard. Hold can 10-14 inches from surface. Apply several light passes a few minutes apart to avoid drips and runs. A single coat is sufficient for optimal performance.

NOTE: Do not use with V2116838 High Temperature Aluminum or V2176838 High Temperature black.

CLEAN UP

Clean valve by turning can upside down and spray for 5 seconds. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as xylene. Do not insert any object into can valve opening.



TECHNICAL DATA

V2100 SYSTEM RUST REFORMER®

PHYSICAL PROPERTIES

		RUST REFORMER®
Resin Type		Modified Alkyd
Pigment Type		Corrosion Inhibitive Pigment, Magnesium Silicate, Carbon Black, Calcium Carbonate
Solvents		Acetone, Ethylbenzene, N-Butane, N-Butyl Acetate, Xylene
MIR		Maximum value of 1.2
Fill Weight		15 oz. (426 grams)
Recommended Dry Film Thickness (DFT) Per Coat		1.0-2.0 mils (25-50µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		Approximately 14 sq.ft./can (1.3 m ²)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	6-12 minutes
	Handle	1-2 hours
	Top Coat	24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Warning!	<p>THIS PRODUCT CONTAINS A CHEMICAL KNOWN TO THE STATE OF CALIFORNIA TO CAUSE CANCER AND BIRTH DEFECTS OR OTHER REPRODUCTIVE HARM. DANGER! EXTREMELY FLAMMABLE, MAY CAUSE FLASH FIRE, CONTENTS UNDER PRESSURE, VAPOR HARMFUL, FOR INDUSTRIAL OR COMMERCIAL USE ONLY. SEE THE PRODUCT MATERIAL SAFETY DATA SHEET (MSDS) AND LABEL WARNINGS FOR ADDITIONAL SAFETY INFORMATION.</p>	
Safety Information	For additional information, see SDS	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.