



PAINTER'S TOUCH® 2X ULTRA COVER® PRIMER SPRAYS

DESCRIPTION AND USES

Painter's Touch® 2x Ultra Cover® Primers provide a sound base for application of Painter's Touch 2X Ultra Cover Enamels on wood, metal, plastic and more. Use of primers promotes topcoat adhesion and helps prevent chipping, cracking and peeling. Use of these primers eliminates the need for multiple coats of enamel finish. Rust-Oleum Painter's Touch 2X Ultra Cover Primer Sprays feature an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. Contains a comfort spray tip with a wider finger pad to reduce fatigue caused by continuous spraying.

TIP: Some plastics made of polyethylene such as plastic storage containers are manufactured in a way that may hinder maximum paint adhesion. Test paint in a hidden area first.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
334018	Red Primer
334017	Gray Primer
249846	Black Primer
334019	White Primer

PRODUCT APPLICATION

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

STEEL: Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated previous coatings.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. The Painter's Touch 2X Ultra Cover Primers are compatible with most coatings, but a test patch is suggested.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not use on objects that may exceed 200°F (93°C) surface temperature. Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE CAN.** Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply multiple light coats versus one heavy coat. Wet sand on metal and dry sand on wood too achieve the smoothest, most uniform base for the topcoat. Use #400 grit wet or dry sandpaper. For best results, let dry at least 30 minutes before wet sanding. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes, to handle in 1 hour and is fully dry in 24 hours. Apply a second coat of primer or Painter's Touch 2X Ultra Cover Enamel within 1 hour or after 24 hours.

NOTE: On plastic maximum paint adhesion and durability is achieved in 5-7 days.

CLEAN-UP

When finished spraying, wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick pin or other object into the stem.

	TECHNICAL DATA	PT2X-03
	PAINTER'S TOUCH[®] 2X ULTRA COVER[®] PRIMER SPRAYS	

PHYSICAL PROPERTIES

		2X ULTRA COVER ULTRA PRIMER SPRAYS
Resin Type		Acrylic Modified Alkyd
Pigment Type		Varies by color
Solvents		Acetone, Naptha, Xylene, N-butyl Acetate
MIR		Max 0.70
Fill Weight		12 oz.
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.5 mils (37.5-62.5µ)
Practical Coverage at Recommended DFT (assume 15% material loss)		10-12 sq. ft./can (0.9-1.1 m ² /l)
Dry Times at 70F (21°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	Within 1 hour or after 24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.